

VICAIMA STANDARD PRIMED FINISH – PAINTING RECOMMENDATIONS

Vicaima roller applied standard primer is water based and is designed to give a thorough base coat for further paint application. Limited grain appearance will usually still be visible when doors are received, but with further paint application as below will ensure a good finish is achieved.

SUBSEQUENT PAINTING

The primed finish will require “light sanding” in the first instance, this is always a procedure when painting and will be best carried out with an orbital sander with a glass paper (150-180 grade). This “light sanding” procedure should only take 1-2 minutes per side, wipe off any dust before proceeding. It is then recommended to use two coats of good quality undercoat and lightly “de-nib” between coats and when fully dry, apply one or two top coats as necessary. We would always recommend carrying out a paint trial prior to commencement of work, to ensure the correct paint application is used.

NB; - Vicaima recommend the use of Aqua Surf 136, which is a water based primer undercoat to ensure adequate coverage.

Notes: As we are constantly improving our product range, we reserve the right to make changes without prior notice.